

⑫ 公開特許公報 (A)

昭58—84980

⑤ Int. Cl. ³	識別記号	庁内整理番号	⑬ 公開 昭和58年(1983)5月21日
C 23 F 7/10		7511—4K	発明の数 1
7/26	1 0 1	7511—4K	審査請求 未請求
// B 05 D 7/14		7048—4F	
C 09 D 5/08		6516—4J	(全 6 頁)

⑭ 溶接性塗装鋼板

市川市高谷新町7番地の1日新
製鋼株式会社製品研究開発セン
ター内

⑯ 特 願 昭56—184127

⑰ 出 願 日 昭56(1981)11月17日
3/3 (1/1 PAJ) - (C) PAJ / JPO

⑱ 発 明 者 横山雅俊

PN - JP58084980 A 19830521
AP - JP19810184127 19811117
PA - NITSUSHIN SEIKOU KK
IN - TAKAMURA HISAO; others: 05
I - C23F7/10 ; C23F7/26
SI - B05D7/14 ; C09D5/08
TI - WELDABLE PAINTED STEEL PLATE
AB - PURPOSE: To provide a steel plate painted on one side which is provided with weldability and corrosion preventiveness on paint films by forming mixed phosphates of specific compsns. on the surface of the steel plate then providing an undercoating layer of specific chromate type and a zinc-contg. top coating layer thereon.
- CONSTITUTION: A film of mixed phosphates mixed with iron phosphate and zinc phosphate-iron is formed on the surface of a steel plate regulated to 4-20 μ surface roughness in a 1-500mg/m² range. A stabilized aq. soln. for coating consisting of 10pts.wt. chromium trioxide wherein the ratio of content of hexavalent chromium/content of chromium oxide attains 0-2.3, 3-4 parts phosphoric acid (100% H₃PO₄), 17-20 parts an acrylic emulsion polymer in solid contents, and 200-4,000 parts water is coated on said film and is dried, whereby an undercoating layer of 5-1,000mg/m² total content of Cr is formed. The top coating layer of the resin contg. zinc powder is formed on the undercoating layer in a 10-50 μ range. This painted steel plate has excellent corrosion preventiveness, electric weldability and paint adhesive strength.
GR - C180
ABV - 007181
ABD - 19830810

鋼の状態に還元され、6価クロム量/3価クロム量の比が0～2.3となつた三酸化クロム10重量部、リン酸(100% H₃PO₄)3～4重量部、ポリアクリル酸4～5重量部、アクリルエマルジョン重合体固形分17～20重量部および水溶液にするための水200～4000重量部を含む金属表面被覆用安定水溶液を塗布乾燥した下塗層が全クロム量として5～100%、またこの下塗層の上に亜鉛粉末を含有する樹脂の上塗層が10～50 μ それぞれ形成されていることを特徴とする溶接性塗装鋼板。

3. 発明の詳細な説明

電気亜鉛めつき鋼板や片面溶融亜鉛めつき鋼板などのめつき鋼板が使用されていたが、生産能率が低いとか、工程数が多くなるとかの理由により高価になるという欠点があつた。

このため、近年安価に製造できる片面防食鋼板として、塗膜に溶接性と防食性を付与した片面塗装鋼板が検討されている。

本発明者らはこの種の塗装鋼板として、先に表面粗度が4～20 μ の鋼板表面に、40～50%が3価状態に還元されている三酸化クロム10重量部、リン酸(100% H₃PO₄)3～4重量部、ポリアクリル酸4～5重量部、アクリルエマルジョン